

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (original) A method of detackifying an edge face of a roll of pressure sensitive adhesive tape, said method comprising:
  - a) contacting an edge face of the roll of tape with a non-free radically curable composition comprising:
    - i) water, and
    - ii) film-forming agent; and
  - b) drying said composition.
2. (original) The method of claim 1, wherein said film-forming agent comprises a polymer is selected from the group consisting of ethylene vinyl acetate, polyvinyl acetate, polyvinyl chloride, cellulose and combinations thereof.
3. (original) The method of claim 1, wherein said film-forming agent comprises polyurethane.
4. (original) The method of claim 1, wherein said film-forming agent comprises acrylic resin.
5. (original) The method of claim 1, wherein said film-forming agent is selected from the group consisting of wax and silicone.
6. (original) The method of claim 1, wherein said film-forming agent comprises polyethylene wax.

7. (original) The method of claim 4, wherein said composition further comprises metal alkyl salt.
8. (original) The method of claim 6, wherein said composition further comprises metal alkyl salt.
9. (original) The method of claim 1, wherein said composition further comprises fumed silica.
10. (original) The method of claim 1, wherein said tape comprises a backing comprising a polymer and a pressure sensitive adhesive composition comprising rubber.
11. (original) The method of claim 10, wherein said backing comprises vinyl.
12. (original) The method of claim 1, wherein said tape comprises  
a backing comprising a polymer impregnated fiber scrim, and  
a pressure sensitive adhesive composition comprising rubber disposed on  
said backing.
13. (original) The method of claim 1, wherein said tape comprises a backing comprising cellulose.
14. (original) The method of claim 1, wherein said tape comprises a release liner.
15. (original) The method of claim 14, wherein said release liner comprises polyethylene terephthalate.

16. (original) The method of claim 1 further comprising  
contacting a second edge face of said roll of tape with a composition  
comprising water and film-forming agent; and  
drying said composition.
17. (original) The method of claim 16, further comprising substantially  
simultaneously:  
contacting said first edge face with a coating composition, and  
contacting said second edge face with a coating composition.
- 18-39. (canceled).
40. (original) A method of detackifying an edge face of a roll of pressure sensitive  
adhesive tape, said method comprising:  
a) contacting an edge face of the roll of tape with a hot melt composition  
comprising wax; and  
b) solidifying said composition.
41. (original) The method of claim 40, wherein the average melting point of said wax  
is at least about 90°C.
42. (original) The method of claim 41, wherein said wax is selected from the group  
consisting of ethylene homopolymer wax, microcrystalline wax, polyethylene homopolymer wax,  
micronized polyolefin wax and combinations thereof.